

AKLP-SD-99 / AKLP-SD-98

Qo'shimcha (metallurgiya, payvandlash)

BELGILANISHLAR

EN AW AKLP-SD-99 / AKLP-SD-98	ASTM / US —	DIAMETRLAR 9.5; 12; 15 mm	Σ , MPA не более 180
---	----------------	-------------------------------------	---------------------------------------

QO'LLANISH SOHASI

Po'lat quyish uchun deoksidlovchi — uzluksiz quyish va yuqori sifatli metallurgik jarayonlar.

AFZALLIKLAR

- Uzluksiz quyish uchun yuqori tozalik
- Turli jarayonlar uchun SD-99 va SD-98 markalari
- Nazorat ostidagi mustahkamlik
- Standart hajmdagi g'altaklarda yetkazib beriladi

YETKAZIB BERISH HOLATLARI

HOLAT	DIAMETR, MM	MUSTAHKAMLIK CHEGARASI, MPA	CHO'ZILISH, MIN, %	SOLISHTIRMA QARSHILIK, MAKS, $\Omega \cdot \text{MM}^2/\text{M}$	O'TKAZUVCHANLIK, MIN, % IACS
F	9.5; 12; 15	не более 180	—	—	—

Alusilk

PART OF ITS GROUP

Coiled Aluminium · Connected Future

BOSH OFIS

Dubai Silicon Oasis, Dubai, UAE
+971 50 153 0202
info@alusilk.ae

O'ZBEKISTONDAGI FILIAL

Abdulla Qodiriy ko'chasi, 7 · Yunusobod tumani
· Toshkent
+998 97 341 2222
alusilk.uz · alusilk.ae